

PCTFE

| Properties | Norm | Value | Unit |
|---|------------|-------------|----------------------|
| Mechanical properties | | | |
| Hardness shore D | DIN 53 505 | 72 – 80 | Sh. D. |
| Ball pressure hardness | DIN 53 456 | 65 – 70 | N/mm ² |
| Tensile strength (23°C) | DIN 53 455 | 32 – 40 | N/mm ² |
| Elongation at break (23°C) | DIN 53 455 | 20 – 120 | %min |
| Tensile modulus | DIN 53 457 | 600 – 2000 | N/mm ² |
| Coëff. of friction v-steel – dynamic | -- | 0,35 | -- |
| Physical properties | | | |
| Specific gravity | ISO 12086 | 2,10 – 2,16 | g/cm ³ |
| Water absorption | DIN 53 495 | 0,0 | % |
| Electrical properties | | | |
| Dielectric strength | DIN 53 481 | 50 – 70 | KV/mm |
| Thermal properties | | | |
| Coefficient of thermal expansion (20-100°C) | -- | 5 | 1/K.10 ⁻⁵ |
| Thermal conductivity (23°C) | DIN 52 612 | 0,19 | W/K.m |
| Maximum Continuous operating temperature | -- | 170 | °C |
| Minimum Continuous operating temperature | -- | -273 | °C |

Disclaimer: Information contained in this data sheet is up-to-date and correct as at the date of issue. The given information is only informative and we cannot guarantee the accuracy nor can we take any accountability for the use of this information. The customer is responsible for the quality of products and has to test usage and processing to use. Some values are based on the datasheet of the supplier, internal tests and research. The values are guideline values that can be used for comparison for material selection.

Vanéflon n.v./s.a.
Industrieterrein Zwaarveld 12
B – 9220 Hamme

Tel: +32 52 47 63 99
Fax: +32 52 47 68 64

Email: info@vaneflon.be
Web: www.vaneflon.com